

TECHNICAL DATA SHEET

EGGER MDF-MBP-L E1 CE

Recipe: 513

Application: This is a board that has particularly good deep milling properties due to a fine fibre quality (MB). It is more densely compacted, significantly improved with regard to its resistance to cracking and its conductivity has been increased through the addition of a halogen-free conductivity additive (L). This type of board is particularly suited for coating processes with powder coating.



Board type meets EN 622-5 standard

Mechanical properties Board mean values	Unit	Board thickness		
		>12 - 19	>19 - 30	>30 - 40
Density	[kg/m ³]	Plant specific		
Internal Bond strength EN 319	[N/mm ²]	≥ 1,0	≥ 0,85	≥ 0,75
Bending strength EN 310	[N/mm ²]	≥ 28	≥ 24	≥ 19
Modulus of elasticity EN 310	[N/mm ²]	≥ 2900	≥ 2500	≥ 2100
Swelling in thickness 24h EN 317	[%]	≤ 8	≤ 7	≤ 6
Surface soundness EN 311	[N/mm ²]	≥ 1,2		
Screw withdrawal surface	[N]	≥ 1250		
Screw withdrawal edge	[N]	≥ 1080	≥ 1000	≥ 940
Sand content	[%]	≤ 0,02		
Moisture content *1 EN 322	[%]	6±1		
Surface absorption	[mm]	180		
Formaldehyde content *2 EN 120	[mg/100g]	E1		
Surface resistance Rs *3	[Ω]	ca. 1x 10 ¹⁰		
Volume resistance Ro	[Ω]	ca. 1x 10 ¹⁰		

General tolerances	Unit	Board thickness		
		>12 - 19	>19 - 30	>30 - 40
Length tolerance EN 324	[mm]	±2,0mm/m, maximum ±5,0		
Width tolerance EN 324	[mm]	±2,0mm/m, maximum ±5,0		
Squareness EN 324	[mm/m]	≤2,0		
Edge straightness EN 324	[mm/m]	≤1,5		
Thickness tolerance EN 324	[mm]	±0,2	±0,3	±0,3
Standard sanding		K220		
Bowing	[mm/m]	< 1,5 mm		

Building physical properties	Unit	Board thickness		
	[mm]	>12 - 19	>19 - 30	>30 - 40
Fire behaviour category				
Board thickness \geq 9 mm and density \geq 600 kg/m ³ in line with EN 13986		D-s2, d0		
Water vapour diffusion resistance value EN 13986				
		μ moist	μ dry	
Mean density 600 kg/m ³		12	20	
Mean density 800 kg/m ³		20	30	
Thermal conductivity EN 13986				
Mean density 600 kg/m ³	W/(m·K)	0,10		
Mean density 800 kg/m ³		0,14		
Air sound insulation EN 13986				
EN 13986		$R = 13 \times \lg(m_A) + 14$ (m_A = board surface weight kg/m ²)		
Sound absorption EN 13986				
Frequency range				
250 Hz bis 500 Hz		0,10		
1000 Hz bis 2000 Hz		0,20		
Biological durability EN 13986				
EN 335-3		Harzard category 1 (no earth contact , dry 20%/65% relative humidity)		
PCP content EN 13986				
EN 13986	[ppm]	<5		

*1 On delivery

*2 Formaldehyde content

According to the "Regulation on the Prohibition of Chemicals (ChemVerbotsV)" annex to § 1, clause 3 from 14th October, 1993 in connection with the publication of the BGA in the federal health sheet 10/91 (s. 487-489) about "testing method for particleboard", uncoated MDF board must not exceed a perforator limit value (photometrical) of 8 mg HCHO/100g over-dry board at moisture content of 6,5 %. The flexible half-years mean value is max. 7 mg HCHO/100g over-dry board.

*3 Surface resistance Rs

The noted value of electrical resistance Rs is valid for boards with Moisture content \geq 5%. By lower Moisture content is the electrical resistance negative affected.

Provisional note:

This technical data sheet has been carefully drawn up to the best of our knowledge. We accept no liability for any mistakes, errors in standards or printing errors. In addition, technical modifications can result from the continuous further development, as well as from changes in standards and documents originating from statutory bodies. The contents of this technical leaflet should therefore not be considered as instructions for use or as legally binding.