

## CE DECLARATION OF PERFORMANCE

according to Regulation (EU) No. 305 of the European Parliament and the Council of 9 March 2011

DOP no.	DOP-737-03
1 Unique product identification code:	737 (recipe no.) 6 to 40 mm (panel thickness)
2 Use:	Structural or load-bearing components for indoor use in dry and humid conditions
3 Name and Manufacturer Registered trade name or registered brand and contact address of the manufacturer:	<b>EGGER OSB 3</b>  SC EGGER România SRL Str. Austriei 2 RO-725400 Rădăuți, jud. Suceava web: <a href="http://www.egger.com">www.egger.com</a>
4 not applicable	
5 System for the assessment and verification of constancy of performance of the building product:	System 2+
6 Harmonized standard:	EN 13986:2004+A1:2015
Notified body:	no. 0766  eph – Entwicklungs- und Prüflabor Holztechnologie GmbH Zellerscher Weg 24 D-01217 Dresden web: <a href="http://www.eph-dresden.com">www.eph-dresden.com</a>

7 Declared performance:


Specification		Panel thickness [mm]							
		unit	> 6 - 10	> 10 - <18	18 - 25	> 25 - 32	>32 - 40		
Bending strength	acc. to EN 310 - 0° major axis o°	N/mm <sup>2</sup>	≥ 22	≥ 20	≥ 18	≥ 16	≥ 14	OSB/3 acc.to EN 300	
	acc. to EN 310 – 90° minor axis	N/mm <sup>2</sup>	≥ 11	≥ 10	≥ 9	≥ 8	≥ 7		
Modulus of Elasticity	acc. to EN 310 - 0° major axis o°	N/mm <sup>2</sup>	≥ 3500	≥ 3500	≥ 3500	≥ 3500	≥ 3500		
	acc. to EN 310– 90° minor axis	N/mm <sup>2</sup>	≥ 1400	≥ 1400	≥ 1400	≥ 1400	≥ 1400		
Essential characteristics		unit	Panel thickness [mm]					Harmonized technical specification	
Durability	thickness swelling 24h	%	≤ 15						EN 13986:2004+A1:2015
	Internal bond	N/mm <sup>2</sup>	≥ 0,34	≥ 0,32	≥ 0,30	≥ 0,29	≥ 0,26		
	internal bond - option 1	N/mm <sup>2</sup>	≥ 0,18	≥ 0,15	≥ 0,13	≥ 0,10	≥ 0,08		
	bending strength - major axis - option 1	N/mm <sup>2</sup>	≥ 9	≥ 8	≥ 7	≥ 6	≥ 6		
	mechanical		k <sub>def</sub>	k <sub>mod permanent</sub>	k <sub>mod long</sub>	k <sub>mod medium</sub>	k <sub>mod short</sub>	k <sub>mod instantenous</sub>	
		SC1	1,50	0,40	0,50	0,70	0,90	1,10	
		SC2	2,25	0,30	0,40	0,55	0,70	0,90	
	biological ( use class)		Use class 1 & 2						
Release of Formaldehyde	acc. to EN 717-1	ppm	≤ 0,10 - emission class E1						
Release of PCP		ppm	< 3,0						
Density		kg/m <sup>3</sup>	≥ 600						
Water vapour permeability	μ (dry / wet)	-	200 / 150						
Thermal conductivity		W/mK	0,13						
Airborne sound insulation	sound absorption coefficient	-	0,10 / 0,25 (frequency range 250 - 500 Hz / 1000-2000 Hz)						
	sound insulation R	dB	R = 13 * lg(m <sub>A</sub> ) + 14 (area mass related m <sub>A</sub> , frequency range 1 to 3 kHz)						
Air permeability	acc. to EN 12114 (at 50Pa pressure difference)	m/(m <sup>2</sup> * h)	NPD						
Reaction to fire *)		class	class floor covering	Minimum thickness [mm]					
	without air gap behind OSB a,b,e,f	D-s2, d0	D <sub>fl,s1</sub>	9 mm					
	with closed air gap or open air gap ≤ 22mm behind OSB c,e,f	D-s2, d0	-	9 mm					
	with closed air gap behind OSB d,e,f	D-s2, d0	D <sub>fl,s1</sub>	15 mm					
	with open air gap behind OSB d,e,f	D-s2, d0	D <sub>fl,s1</sub>	18 mm					
	without restriction e,f	E	E <sub>fl</sub>	3 mm					

Essential characteristics		unit	panel thickness [mm]					Harmonized technical specification
			> 6 - 10	> 10 - <18	18 - 25	> 25 - 32	>32 - 40	
<b>Characteristic strength</b>								EN 13986:2004+A1:2015
<b>Bending <math>f_m</math></b>	0° - major axis	N/mm <sup>2</sup>	18,0	16,4	14,8	NPD	NPD	
	90° - minor axis	N/mm <sup>2</sup>	9,0	8,2	7,4	NPD	NPD	
<b>Tension <math>f_t</math></b>	0° - major axis	N/mm <sup>2</sup>	9,9	9,4	9,0	NPD	NPD	
	90° - minor axis	N/mm <sup>2</sup>	7,2	7,0	6,8	NPD	NPD	
<b>Compression <math>f_c</math></b>	0° - major axis	N/mm <sup>2</sup>	15,9	15,4	14,8	NPD	NPD	
	90° - minor axis	N/mm <sup>2</sup>	12,9	12,7	12,4	NPD	NPD	
<b>Shear <math>f_v \perp</math> panel surface</b>	0° - major axis / 90° - minor axis	N/mm <sup>2</sup>	6,8	6,8	6,8	NPD	NPD	
	0° - major axis / 90° - minor axis	N/mm <sup>2</sup>	1,0	1,0	1,0	NPD	NPD	
<b>Mean stiffness</b>								
<b>Bending <math>E_m</math></b>	0° - major axis	N/mm <sup>2</sup>	4930	4930	4930	NPD	NPD	
	90° - minor axis	N/mm <sup>2</sup>	1980	1980	1980	NPD	NPD	
<b>Tension <math>E_t</math></b>	0° - major axis	N/mm <sup>2</sup>	3800	3800	3800	NPD	NPD	
	90° - minor axis	N/mm <sup>2</sup>	3000	3000	3000	NPD	NPD	
<b>Compression <math>E_c</math></b>	0° - major axis	N/mm <sup>2</sup>	3800	3800	3800	NPD	NPD	
	90° - minor axis	N/mm <sup>2</sup>	3000	3000	3000	NPD	NPD	
<b>Shear <math>G_v \perp</math> panel surface</b>	0° - major axis / 90° - minor axis	N/mm <sup>2</sup>	1080	1080	1080	NPD	NPD	
<b>Shear <math>G_{in}</math> in panel surface</b>	0° - major axis / 90° - minor axis	N/mm <sup>2</sup>	50	50	50	NPD	NPD	
<b>Impact resistance</b>		N/mm <sup>2</sup>	NPD	NPD	NPD	NPD	NPD	
<b>Embedding strength</b>		N/mm <sup>2</sup>	EN 1995-1-1, Abs. 8					
<b>Racking resistance</b>		N/mm <sup>2</sup>	EN 1995-1-1					
<b>Performance wall</b> EN 12871	soft body impact acc. to EN 596	-	Pass					
	panel thickness	mm	≥ 9 mm					
<b>Performance Floor</b> EN 12871 (major axis, 0°)	load category	-		A	A			
	panel thickness	mm		≥ 15	≥ 18			
	cc-span	mm		≤ 410	≤ 625			
<b>Performance roof</b> EN 12871 (major axis, 0°)	load category	-		H	H			
	panel thickness	mm		≥ 12	≥ 18			
	cc-span	mm		≤ 625	≤ 833			

8 not applicable

The product performance according to number 1 corresponds to the declared performance according to number 7. Solely the manufacturer is responsible for drafting the declaration of performance according to number 3.

Signed for and in the name of the manufacturer by:

A handwritten signature in blue ink, consisting of a large, stylized 'P' followed by a horizontal line and a small flourish.

Christoph Pirckmayer  
Plant Manager Technical/Production OSB

Rădăuți, 07.01.2025

---

\*) Note:

- a Without air gap installed directly on products in classes A1 or A2-s1, d0 with a minimum raw density of 10 kg/m<sup>3</sup> or at least products of class D-s2, d2 with a minimum raw density of 400 kg/m<sup>3</sup>.
- b An underlayment made of cellulose thermal insulation material of at least class E may be used if installed directly behind the wood-based material; however, this does not apply to flooring.
- c Installed with air gap behind, the product bordering with its rear side the empty space must correspond at least to class A2-s1,d0 with a minimum raw density of 10 kg/m<sup>3</sup>.
- d Installed with air gap behind, the product bordering with its rear side the empty space must correspond at least to class D-s2,d2 with a minimum raw density of 400 kg/m<sup>3</sup>.
- e With the exception of flooring, the class also corresponds to veneered, phenol and melamine-faced boards.
- f A vapour barrier with a thickness of up to 0.4 mm and a mass of up to 200 g/m<sup>2</sup> may be installed between the wood-based material and the underlayment if there is no air gap in between.