

Technical data sheet

EGGER Eurodekor

Material description: EGGER Eurodekor materials are melamine faced wood based boards for interior applications such as furniture and interior decoration.

Possible substrates: EGGER Eurospan raw chipboard, EGGER MDF, EGGER Eurolight lightweight board or EGGER OSB Combiline



Surface properties according to EN14322

Surface properties	Test method	Unit	Value	
Surface defects				
• points	EN 14323	[mm ² /m ²]	≤2	
• length	EN 14323	[mm/m ²]	≤20	
Resistance to scratching	EN 14323	[N]	≥1,5 ^{*1)}	
Resistance to staining	EN 14323	[level]	≥3	
Resistance to cracking	EN 14323	[level]	≥3	
Resistance to abrasion Depending in the layer configuration different classes are researched	EN 14323	[Revolutions]	Class	IP
			1 (print décor incl. pearlescent)	<50
			2	≥50
			3A (print decors with overlay)	≥150
			3B (solid decors <120 g/m ²)	≥250
4 (solid decors ≥120 g/m ²)	≥350			

Dimensional properties according to EN14322

	Test method	Unit	Thickness range (nominal thickness)		
			<15mm	15 up to 20mm	>20 mm
Thickness					
• Standard boards	EN 14323	[mm]	±0,3	±0,3	±0,5
• Boards with multi-layer surface total thickness ^{*2)}	EN 14323	[mm]	+0,5/-0,3	+0,5/-0,3	±0,5
Length and width					
• commercial available size	EN 14323	[mm]	±5	±5	±5
• pre-cut panels	EN 14323	[mm]	±2,5	±2,5	±2,5
Flatness	EN 14323	[mm/m]	--	≤2 ^{*3)}	≤2 ^{*3)}
Edge damage					
• commercial available size	EN 14323	[mm]	≤10	≤10	≤10
• pre-cut panels	EN 14323	[mm]	≤3	≤3	≤3

Fire behaviour

	Core board/Substrate	Single layer		Classification acc. to EN13986
Eurodekor raw chipboard	Eurospan raw chipboard (density $\geq 600 \text{ kg/m}^3$)	X		D-s2, d0 ($\geq 9\text{mm}$)
Eurodekor MDF	MDF (density $\geq 600 \text{ kg/m}^3$)	X		D-s2, d0 ($\geq 9\text{mm}$)
	Core board/Substrate	Single layer	Multi-layer	Classification acc. to EN13501-1
Eurodekor Flammex	Eurospan Flammex chipboard	X		B-s1,d0 (12-38mm)
Eurodekor Plus Flammex	Eurospan Flammex chipboard		X*4) X*4)	B-s2,d0 (12- <18mm) B-s1,d0 ($\geq 18\text{mm}$)
Eurodekor MDF Flammex	MDF Flammex	X		B-s1,d0 (10-25mm)

*1) Scratch resistance: Not including decors with pearlescent effect.

*2) Tolerances total thickness: The total thickness is defined as the substrate thickness including the coatings on both sides of the boards.

*3) Flatness: Valid for equally balanced weight of decorative papers on both sides.

*4) Flammex: Not including multilayer boards with white underlay papers.

Formaldehyde emission classes

The Formaldehyde emission classes depend on the used substrate. Information in regards to the Formaldehyde emission of your preferred substrate can be found in the technical datasheets of our substrates. Please visit www.egger.com for further information.

Colour matching and surface texture

Since slight variations in colour will occur due to inherent variation in the surfacing papers and the substrate, we recommend that components which are used side by side should be selected from the same production batch to ensure colour compatibility.

A slight deviation of color and surface finish according to Class 4 EN14323 between the EGGER reference sample and the test specimen is permitted. For pearlescent and metallic decors, a deviation of Class 3 acc. to EN14323 is permitted.

Resistance against heat

The resistance against heat of Eurodekor materials differs between long and short periods of heat exposure. For long and continuous periods of heat exposure, a maximum temperature of 50°C (122°F) is applicable. We kindly advise that continuous exposure in temperatures of over 50°C (122°F) may result in surface defects such as cracks.

Installations of technical equipment that emit heat, for instance laptops, require an appropriate distance between heat source and melamine surface to avoid heat accumulation and allow air and temperature circulation.

General information

Careful checks of incoming materials is an essential part of any commercial transaction. EGGER recommends proceeding with these checks according to common statistical methods. Handling and storage of Eurodekor melamine faced boards has to be done with care. The boards should advisably be stored on a flat and dry base in a closed building. The panels must be stored in a frost-protected surrounding, preferred within temperature of 20°C (68°F) and 65% relative humidity. For storage in divergent conditions, we recommend additional packaging of the materials such as shrink-wrapping to ensure stable quality. We recommend conditioning the final products according to the expected in-room climate prior to installation. For further information, please visit www.egger.com.

Provisional note:

This technical data sheet has been carefully drawn up to the best of our knowledge. It is intended for information only and does not constitute a guarantee in terms of product properties or its suitability for specific applications. It is based on practical experiences, our own tests and correspond to our present state of knowledge. We accept no liability for any mistakes, errors in standards, or printing errors. In addition, technical modifications may result from the continuous development of EGGER Eurodekor, as well as from changes to standards and public law documents. Therefore, the content of these processing instructions cannot serve as instructions for use nor as a legally binding basis.

