

TECHNICAL DATA SHEET

EUROSPAN® E1 P2 CE

Recipe: 1

Application: Base particle board for interior fitments (including furniture) for use in dry conditions.



Board type in line with 312-2

Mechanical properties according EN-standard	Unit	Board thickness				
	[mm]	6-13	>13-20	>20-25	>25-35	>32-40
Density	[kg/m ³]	Plant specific				
Internal Bond strength EN 319	[N/mm ²]	0.4	0.35	0.30	0.25	0.20
Bending strength EN 310	[N/mm ²]	11	11	10.5	9.5	8,5
Modulus of elasticity EN 310	[N/mm ²]	1800	1600	1500	1350	1200
Surface soundness EN 311	[N/mm ²]	0,8				
Moisture content *1 EN 322	[%]	5-7				
Formaldehyde content ** EN 120	[mg/100g]	E1				

General Tolerances	Unit	Board thickness				
	[mm]	6-30	>13-20	>20-25	>25-35	>32-40
Length and width tolerance EN 324	[mm]	±5.0				
Squareness EN 324	[mm/m]	≤2.0				
Edge straightness tolerance EN 324	[mm/m]	≤1.5				
Thickness tolerance EN 324 (Sanded boards)	[mm]	±0.3				
Tolerance on the mean density within a board EN 323	[%]	±10				

Building physical properties	Unit	Board thickness				
	[mm]	6-30	>13-20	>20-25	>25-35	>32-40
Fire behaviour category						
Board thickness ≥ 9 mm and density ≥ 600 kg/m ³ in line with EN13986		D-s2, d0 Dfl-s1 (for floorings)				
Water vapour diffusion resistance value						
		μ moist		μ dry		
Mean density 600 kg/m ³		15		50		
Mean density 900 kg/m ³		20		50		
Thermal conductivity EN 13986						
Mean density 600 kg/m ³	W/(m*K)	0.12				
Mean density 900 kg/m ³		0.18				
Air sound insulation EN 13986						
EN 13986		R = 13 x lg(m _A) + 14 (m _A = board surface weight kg/m ²)				
Sound absorption EN 13986						
Frequency range		0.10				
250 Hz to 500 Hz		0.25				
1000 Hz to 2000 Hz						
Biological durability EN 13986						
EN 335-3		Hazard category 1 (no earth contact , dry 20%/65% relative humidity)				
PCP content EN 13986						
EN 13986	[ppm]	< 5				

*1 On delivery

*2 Formaldehyde content:

According to the "Regulation on the Prohibition of Chemicals (ChemVerbotsV)" annex to § 1, clause 3 from 14th October, 1993 in connection with the publication of the BGA in the federal health sheet 10/91 (s. 487-489) about "testing method for particleboard", uncoated particleboard must not exceed a perforator limit value EN 120 (photometrical - EN 120) of 8 mg HCHO/100g over-dry board at moisture content of 6.5 %. The flexible half-years mean value is max. 6,5 mg HCHO/100g over-dry board.

Provisional note:

This technical data sheet has been carefully drawn up to the best of our knowledge. We accept no liability for any mistakes, errors in standards or printing errors. In addition, technical modifications can result from the continuous further development, as well as from changes in standards and documents originating from statutory bodies. The contents of this technical leaflet should therefore not be considered as instructions for use or as legally binding.