

# PRODUCT DATA SHEET

## EGGER OS´Brace™ – H2 Blue

Recipe: 736, (sanded/unsanded)

Material description: OSB/3 board (according EN 300) for use for load bearing purposes under humid conditions. Only the thickness of 6 mm is certified by UTS (University of Technology, Sydney) as “Structural Sheet Bracing Panel” under AS 1684 and AS 1720.1 in Australia. The boards contain chemical additive for protection against termites, emission class – E1, Tests according valid EN-standards. Strength values are average values.

PLANT: WISMAR

## Board type according EN 300

Mechanical properties	Standard	Unit	Requirement			
<b>Board thickness</b>		[mm]	6,0	>6 - 10	>10 - <18	18 - 25
<b>Density</b>	EN 323	[kg/m³]	≥600	≥600	≥600	≥600
<b>Internal bond</b>	EN 319	[N/mm²]	≥0,34	≥0,34	≥0,32	≥0,30
<b>Internal bond after cycle test</b>	EN 321	[N/mm²]	≥0,18	≥0,18	≥0,15	≥0,13
<b>Bending strength major axis</b>	EN 310	[N/mm²]	≥22	≥22	≥20	≥18
<b>Bending strength after cycle test major axis</b>	EN 310	[N/mm²]	≥9	≥9	≥8	≥7
<b>Bending strength minor axis</b>	EN 310	[N/mm²]	≥11	≥11	≥10	≥9
<b>Modulus of elasticity major axis</b>	EN 310	[N/mm²]	≥4500			
<b>Modulus of elasticity minor axis</b>	EN 310	[N/mm²]	≥1800			
<b>Swelling in thickness 24h</b>	EN 317	[%]	≤15			
<b>Tolerance of the mean density</b>	EN 323	[%]	±15			
<b>Moisture content*1</b>	EN 322	[%]	2-12			
<b>Sanding grade</b>			grade 100			
<b>Formaldehyde content *2</b>	EN ISO 12460-5	[mg/100g]	≤8,0			

General tolerances	Standard	Unit	Requirement
<b>Tolerance in length</b>	EN 324-1	[mm]	±3,0
<b>Tolerance in width</b>	EN 324-1	[mm]	±3,0
<b>Tolerance in thickness (sanded)</b>	EN 324-1	[mm]	+/- 0,1 mm target ex sanding machine, +/- 0,2 mm guaranteed ex sanding machine, - 0,2 mm / +0,5 mm guaranteed CIF
<b>Tolerance in thickness (unsanded)</b>	EN 324-1	[mm]	±0,5
<b>Squareness tolerance</b>	EN 324-2	[mm/m]	≤2,0
<b>Edge straightness tolerance</b>	EN 324-2	[mm/m]	≤1,5

Building physical properties	Standard	Unit	Requirement
<b>Thermal conductivity</b>	EN 13986	[W/(m·K)]	0,13
<b>Water vapour permeability (µ-value)</b>	EN ISO 12572	-	200/150 (dry /humid)
<b>Termite treatment</b>	Boards are manufactured using a chemical additive made by Dr. Wolman GmbH containing Permethrin as termite protection. The amount of additive is used according to AS NZS 1604-2, “Minimum Preservative Retention		
<b>H2 - Approval &amp; Registration</b>	Australia 527 70 H2	New South Wales (Appr.-No. 527 70 H2) Queensland (Cert. – No. 993)	
<b>Approval</b>	Australia, 6 mm	1. AS1684 – 1999 SAA National Timber Framing Code 2. AS1720.1 – 1997 SAA Timber Structures Code – Part 1 Design Methods UTS, 30.09.2005 (University of Technology, Sydney)	

\*1) When dispatched

\*2) Perforator value according EN ISO 12460-5  
according “DIBt-recommendation 100” from June 1994 are the allowed values:  
half year average value: 6,5mg HCHO/100g abs. dry board  
single value: 8,0mg HCHO/100g abs. dry board