

| TECHNICAL DATASHEET  |   |   |
|--|---|---|
| EGGER PRO LAMINATE FLOORING                                      |   | 8/32 WV2 Classic  |
| Coreboard  | E1<br>HCHO  | HDF swell stopp plus  |
| Profile  | JUST clic!<br>Patented  | The patented EGGER installation system JUST clic! stands for quick and simple installation process without glue. Patented as JUST clic! EP 1 441 087 and EP 1 462 587 |
| Guarantee domestic area  | 20  | according to Egger Guarantee  |
| Guarantee comercial area   | 5   | according to Egger Guarantee  |
| Antistatic properties according EN1815                           | Antistatic  | yes, < 2 kV   |
| Class of use   | 32  |   |
| European Norm EN13329  | EN 13329-32   |   |
| Format   | CLASSIC   |   |
| Dimension mm (length x width)                                    | 1292 x 192  |   |
| Complete thickness   | 8   |   |
| Thickness of silenzio® special cellulose                         |   |   |
| Bevel  | WV2   |   |
| Profil   |   |   |
| Pallet   | <b>Packaging</b><br>One-way-pallet                                |   |
| <b>Paket information</b>   |   |   |
|  | Piece   | 8   |
|  | m2  | 1,98  |
|  | kg  | 14,46   |
| <b>Pallet information</b>  |   |   |
|  | Piece   | 480   |
|  | m2  | 119,07  |
|  | kg  | 877,00  |
| <b>Classification and general requirements according EN13329</b> |   |   |
| Abrasion resistance according EN13329, annex E                   | AC4 (IP ≥ 4000)   |   |
| Impact resistance according EN13329, annex H                     | Big ball: ≥ 750 mm<br>Small ball: ≥ 12 N                          |   |
| Resistance to staining EN438                                     | Group 1 + 2: level 5<br>group 3: level 4                          |   |
| Effect of furniture leg according EN424                          | No damage shall be visible, when tested with foot Type 0 artefact |   |
| Effect of a castor chair according EN425 (Type W)                | No change in appearance or damage                                 |   |
| Thickness swelling according ISO 24336                           | ≤ 18 %  |   |
| Tolerance of top layer according EN13329                         | length ± 0,5 mm<br>width ± 0,1 mm<br>thickness ± 0,5 mm           |   |
| Light fastness according EN13329                                 | grey scale ≥ level 4 (EN:20105-A02)                               |   |
| Static indentation by constant pressure according EN ISO 24343-1 | < 0,05  |   |
| Surface soundness according EN13329, annex D                     | ≥ 1,25 N/mm2  |   |
| Thermal resistance according to EN 12667                         | 0,07 m² K/W   |   |

